



## CH0500

|               |                           |
|---------------|---------------------------|
| Content       | 500 cc                    |
| Top out       | 145x121 mm                |
| Top in        | 131x106 mm                |
| Bottom        | 108x84 mm                 |
| Useful Height | 45 mm                     |
| Height        | 55 mm                     |
| Nett weight   | 7,20 gr                   |
| Thickness     | 60 µm                     |
| Alloy         | 8666 H25 / 8006 H24       |
| Lubrification | 300-400 gr/m <sup>2</sup> |

| Packaging   | Quantity<br>ctn | Dimensions Ctn |            |            | Tare Ctn<br>(kg) | Net Ctn<br>(kg) | Gross Ctn<br>(kg) | Ctn/Layer | Layer/Pal | Ctn/Pal   | Quantity<br>palet | Height Pal<br>(m) | Gross Pal<br>(kg) |
|-------------|-----------------|----------------|------------|------------|------------------|-----------------|-------------------|-----------|-----------|-----------|-------------------|-------------------|-------------------|
|             |                 | L(mm)          | W(mm)      | H(mm)      |                  |                 |                   |           |           |           |                   |                   |                   |
| <b>1000</b> | <b>1.000</b>    | <b>425</b>     | <b>350</b> | <b>470</b> | <b>0,77</b>      | <b>7,20</b>     | <b>7,97</b>       | <b>6</b>  | <b>4</b>  | <b>24</b> | <b>24.000</b>     | <b>2,03</b>       | <b>211,28</b>     |
| 10 x 100    | 1.000           | 425            | 350        | 470        | 0,77             | 7,20            | 7,97              | 6         | 4         | 24        | 24.000            | 2,03              | 211,28            |

**Made of materials that complies with :**

- \* Regulation **2004/1935/EC** on material and articles intended to come into **contact with food** and repealing Directive 89/109/EEC
- \* European Standard **EN602** "Aluminium and aluminium alloys - Wrought products - Chemical composition of semi products used for the fabrication of articles for use in **contact with food** (Version 07/2004)"

**Lubrification complies with :**

- \* US Food and Drug Administration FDA21 CFR Ch1 § 172.830 or 178.3910 or 178.3570

**Proper conditions of transport and storage**

- \* Long-term storage at 12-24°C and short-term transport at 10-35°C, in an atmosphere as dry as possible
- \* Avoid moisture (wetness, condensation, ...) and store in closed room as dry as possible.
- \* Allow 2-3 days in intermediate storage, when moving from cold to warm or damp processing rooms.

**Remarks**

- \* Aluminium is a non-toxic metal.
- \* It is recommended to avoid strongly acid and/or saline products
- \* Filling material producer should judge the suitability of the packaging material for each used purpose